

# SUPI Sauna Finish

**DESCRIPTION** Tintable acrylate finish for interior surface treatment of humid rooms. SUPI Sauna Finish forms a dirt and water-repellent surface. Contains fungicides that protect the treated surface.

**EXAMPLES OF USE** Suitable for use on wood, wood fibre board and concrete surfaces according to instructions for use. Especially suitable for walls and ceilings (not for sauna benches) in steam, wash and dressing rooms.

**TECHNICAL DATA** Solids volume: approx. 16 %.  
Density: 1.0 kg/l, ISO 2811  
Thinner: Water  
Base paints: EP  
Gloss grade: semi-matt  
Application method: brush or spray

Colour Range Tikkurila Interior Wood Stains and Lacquers Colour Card.

## INSTRUCTIONS

**Application conditions** The surface to be painted must be dry, the temperature of the air at least +5 °C, and the relative humidity of the air below 80 %.

**Preparation** **New, clean wood surfaces:** Remove all dirt and dust from surfaces. Moisten the surface lightly with a water spray, allow to dry and sand off any protruding wood fibres. Remove the sanding dust.

**Old and dirty or e.g. previously with Supi Sauna Finish treated surfaces:** Wash with Supi Saunapesu Cleaning Agent according to instructions, rinse carefully and allow to dry. Sand if necessary and remove sanding dust.

**Application** Stir SUPI Sauna Finish thoroughly before and occasionally during application.

Treat **steam room** walls once with tinted or colourless Supi Sauna Finish. Thin with water, if necessary.

Steam room walls can also be treated twice with thinned (50% with water) and tinted Supi Sauna Finish. This treatment reduces visible brush marks.

Treat the wood surfaces in **wash and dressing rooms** twice with Supi Sauna Finish. For the first coat thin tinted Supi Sauna Finish with approx. 20 % of water and colourless Supi Sauna Finish only if needed.

Make a test application in an inconspicuous spot to be sure of the correct colour. When thinned the colour appears slightly lighter and translucent than in the colour card. The properties of wood species and previous treatments affect the final colour. Treat small surfaces in one go and large panel surfaces 1-2 panels at a time in order to get a uniform colour.

Preheat the sauna before taking into use and ventilate well.

**Coverage** 8 - 12 m<sup>2</sup>/l.

<b>Drying Times</b>	At 23 <sup>o</sup> C, relative humidity of the air 50 %: Dust dry after approx. 1/2 hour. The next coat can be applied after 2-3 hours. Ready for use in approx. two days.
<b>Cleaning of Tools</b>	Clean tools with soap and water. Tikkurila Pensselipesu (Tool Cleaner) is recommended when cleaning hardened finish from the brush.
<b>Storage</b>	Protect from frost.
<b>ENVIRONMENTAL</b>	Recycle empty, dry cans or dispose them of in accordance with local regulations. Destroy liquid waste according to the local regulations for hazardous waste.
<b>HEALTH AND SAFETY CLASSIFICATION</b> according to EC Directive 99/45/EC	The product is not classified as dangerous. A Safety Data Sheet is available on request.
<b>TRANSPORT CLASSIFICATION</b>	ADR: not classified

sre070612/niear141111/lko141106/tho031106/868 6404